

## PP 熔喷液体过滤材料 PP Meltblown for liquid filtration



可提供不同孔径要求的产品：

Different pore size products can be provided to meet various requirements:

平均孔径 | Mean pore size: 1-100 $\mu$ m

透气度 | Air permeability: 25-5000 L/m<sup>2</sup>·s

- **应用市场：** 饮用水、制药、食品饮料、电子行业等

**Applications:** Drinking water, Pharmaceutical, food & beverage, electronic industries and etc.

- **产品优势 | Advantages:**

采用国际先进生产设备和专利技术确保产品卓越品质。

Utilizing global benchmark production facilities and patented technologies to ensure excellent product quality.

过滤精度高，孔径分布均匀。

High precision and consistent pore size distribution.

### 产品技术参数 | Product Technical Data

#### 1. Micron Filtration Grade

Type	Area Weight (g/m <sup>2</sup> )	Air Permeability* (L/m <sup>2</sup> ·s)	Mean pore size ( $\mu$ m)	Thickness (mm)	Max. Width (mm)
MGL-1	100 $\pm$ 10	3-7	1-2	0.25 $\pm$ 0.03	1500
MGL-2	88 $\pm$ 10	8-12	2-3	0.25 $\pm$ 0.03	
MGL-3	72 $\pm$ 5	20-30	2.5-4.5	0.25 $\pm$ 0.03	
MGL-5	56 $\pm$ 5	30-50	4-7	0.23 $\pm$ 0.03	
MGL-7	53 $\pm$ 5	70-90	6-9	0.23 $\pm$ 0.03	
MGL-10	50 $\pm$ 5	110-130	9-12	0.23 $\pm$ 0.03	

#### 2. Coarse Filtration Grade

Type	Area Weight (g/m <sup>2</sup> )	Air Permeability* (L/m <sup>2</sup> ·s)	Mean pore size ( $\mu$ m)	Thickness (mm)	Max. Width (mm)
MGL-13	40 $\pm$ 3	190-210	12-15	0.22 $\pm$ 0.03	1500
MGL-15	35 $\pm$ 3	200-250	14-17	0.20 $\pm$ 0.03	
MGL-18	50 $\pm$ 5	250-400	17-20	0.4 $\pm$ 0.03	
MGL-20	30 $\pm$ 3	400-600	18-22	0.33 $\pm$ 0.03	
MGL-30	30 $\pm$ 3	1300-1600	28-32	0.33 $\pm$ 0.03	

\* 透气度测试条件 | Air perm. testing condition:  $\Delta P=200$ Pa

请联系名冠获取更多产品型号信息。 | Please contact Mingguan for more product types which not listed in this table.

#### 免责声明/Disclaimer

该资料中产品的公开性能参数不属于对产品质量具有法律约束力的声明。 这些性能参数不会成为合同的组成部分。它们代表在制造时根据适用的测试方法获得的平均值，并受正常生产波动的影响。 产品参数如有更改，恕不另行通知。 如需了解更多产品信息，请联系名冠。

The disclosed performances and measured values of the product in this document are not legally binding statements of product quality. These performances and values will not form part of the contract. They represent average values obtained at the time of manufacture according to applicable test methods and are subject to normal manufacturing variations. The products properties are subject to change without prior notice. Please contact Mingguan for more information.

#### 联系方式 / Contact:

上海名冠净化材料股份有限公司 / Shanghai Mingguan Purification Materials Co., Ltd.

上海市闵行区闵虹路 166 弄中庚环球创意中心 T2-2301/2319 室

Room 2301/2319, T2, Lane. 166, Minhong Road, Minhang District, Shanghai 201102, P. R. China

TEL: +86 21 3350 6325 Email: contact@mingguangroup.com